

PITTARC GTH

SCP
SIAT

Classificazione/Classification

Metallo d'apporto/Weld Metal
EN ISO 16834-A G 62 4 M21

Filo/Wire Electrode
EN ISO 16834-A-G Mn3NiCrMo
AWS A5.28 ER100S-G

Descrizione/Description

Filo pieno per saldatura MIG/MAG (GMAW) legato al Cr-Ni-Mo per l'unione di acciai alto-resistenziali.

MIG/MAG (GMAW) gas shielded welding wires Cr-Ni-Mo alloyed of high strength steels.

Disponibile con i seguenti trattamenti superficiali:

Available with the following surface treatments:

- STANDARD - Ramato/Copper Coated
- GREEN-ARC - Non ramato/Copper Free
- INNOV-ARC - Ramato per alte prestazioni/Copper Coated for High-Performance

Composizione chimica del filo/Wire electrode chemical composition

		C%	Mn%	Si%	Cr%	Ni%	Mo%
PITTARC GTH	(¹)	0,09	1,65	0,75	0,60	0,55	0,27
ISO 16834-A-G	min		1,30	0,60	0,40	0,50	0,15
Mn3NiCrMo	max	0,14	1,80	0,80	0,65	0,65	0,30

(¹) valori tipici / Typical values

Caratteristiche meccaniche del deposito/Mechanical properties all weld metal

	YS	UTS	A5d	KV @ -20°C	KV @ -40°C
	MPa	MPa	%	J	J
PITTARC GTH (²)	700	770	20	100	75
EN ISO 16834-A-G 62 4 M21 Mn3NiCrMo	≥ 620	700 ÷ 890	≥ 18	-	≥ 47
AWS A5.28-ER100S-G	(≥ 610)	≥ 690	(≥ 16)	-	-

(²) valori tipici con gas di protezione M21 / Typical values with shielding gas M21

Gas di protezione/Shielding Gas

EN ISO 14175 : M21 (miscela/mixed gas Ar + 15÷25% CO₂).

Approvazioni/Approvals

CE, DB, TÜV.

Per ulteriori informazioni relative al filo GTH vedere la scheda prodotto di riferimento Doc. SPP112.
For further information concerning the wire type GTH refer to the product data sheet Doc. SPP112.

All data/information of this document are only at informative title and not binding for SIAT S.p.A., who entitles full right to modify/change them without prior notice.

